

## Technical Data Sheet Push Plastic Premium ABS

Specially formulated ABS resin for 3D printing with high flow and high gloss characteristics

Mechanical Properties	Test Method and Units	Value
Izod Notched Impact (1/4", 23°C)	ASTM D256 Kg-cm/cm	22
Tensile Strength at Yield (23°C)	ASTM D638 kg/cm2	481
Flexural Strength at Yield (23°C)	ASTM D790 kg/cm2	668
Flexural Modulus (23°C)	ASTM D790 ×104kg/cm2	2.31
Rockwell Hardness (1/4", 23°C)	ASTM D785 R-Scale	112
Thermal Properties		
Heat Distortion Temperature (1/4", 18.6 kg/cm2)	ASTM D648 °C	87
Heat Distortion Temperature (1/4", 4.6 kg/cm2)	ASTM D648 °C	94
Flammability	UL-94 -	HB(1.5)

## Notes:

<sup>\*</sup> The values presented are laboratory averages and may vary within a moderate range for 3D printed specimens

<sup>\*</sup>This data is not intended to substitute for any testing you may need to determine the suitability of this material

